

## Technical Information

# PC UD

- **PC UD** Is a nonionic defoamer consisting of highly refined mineral oils with additives to provide antifoaming properties will dear resin systems
- **PC UD** is compatible with most standard urethanes, acrylics and latexes and will not cause cratering and fisheyes.
- **PC UD** for use in solvent-based high solids systems and systems based upon alkyds. It has excellent persistence and will not separate. The product is designed to be easy to use and provide economical control of foam in many paint and coating system including water-based acrylics and epoxies.

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE	UNIT
APPEARANCE:	Opaque tan liquid	-
ODOR:	Mild odor	-
VISCOSITY @ 25°C:	40	CPS Brookfield
pH (1% EMULSION):	7.0	-
SOLUBILITY IN H <sub>2</sub> O:	Dispersible	-
SPECIFIC GRAVITY:	0.854	g/ml
POUR POINT:	Approx. -10	°C
FLASH POINT:	~144	°F

**\*NOTE:** Typical properties are not suitable for specification purposes.

### APPLICATIONS :

- Latex coatings and paints
- Overprint varnishes for graphic arts
- Inks (gravure and flexographic)
- Adhesives/glues
- Alkyd Paints
- Epoxies

### ADDITIONAL INFORMATION:

Normal dosage ranges from 0.10 to 0.20% of PC UD based upon formula weight of proposed mixture. For inks, PC UD is normally used at a rate of 0.05 to 0.2% based on the formula weight. It can be added to the pigment grind to control entrained air and aid in the overall wetting of the pigment during the grinding. For adhesives and glues, PC UD is normally used at a rate of 0.02 to 0.2% based on the formula weight

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification. Refer to the Safety Data Sheet (SDS) for health, safety and personal protection.